

Test Report

Photographic Activity Test according to ISO 18916:2007

The material described below has **failed** to pass the Photographic Activity Test PAT for enclosure materials. A successful material must pass all three criteria.

Material description: **Cropper 1.4 mm**
Supplied by: **Oekopack Conservus AG** on **08.10.2015**

Test Results

1. Image Interaction Test

The material shall not produce a percentage image interaction effect in the colloidal silver fade detectors greater than a relative difference of more than $\pm 20\%$ compared to the control.

Density change of control: **-0.92**
Density change of material: **-1.10** Relative difference: **21%**

2. Stain Test

The material shall not produce a mean stain in the photographic paper stain detector that is greater than the mean stain produced by the filter paper controls plus 0.08 density units.

Density change of control: **0.12**
Density change of material: **0.14** Difference: **0.02**


3. Mottle Test

The enclosure material shall not produce *easily recognizable* mottling.


Visual assessment: **Passed** DOMAS Mottle-Index: **0.78** *

Date of testing: **29.10.2015** Sample-ID: **03-018**

Papiertechnische Stiftung, Pirnaer Straße 37, D-01798 Heidenau, Germany



Dr. Antje Harling
Div. Head Materials Testing and Analytics



Dr. Carsten Schönfeld
PAT Project Manager